

**230-2% Neo-Asphalt** (trowel grade)**DESCRIPTION:**

Karnak #230-2% Neo-Asphalt is a cold applied, rubberized asphalt cement, designed especially for use as an adhesive for paving blocks and pressed asphalt bricks. Eliminates the need for a hot kettle.

**PHYSICAL PROPERTIES:**

Viscosity @ 25C:	30,000-40,000 C.P.S.	Softening Point of Base:	200°F
Specific Gravity @ 25C:	1.02	Penetration of Base:	24
Weight per Gallon @ 25C:	8.5 lbs.	Ductility:	130 cm
% Solids by Weight:	70%	% Inorganic Material:	18%
% Solids by Volume:	65%	% Long Fiber:	10%
Flash Point:	107°F	% Neoprene:	2% min.
Softening Point of Rubber Blend:	150°F		

**SURFACE PREPARATION:**

All surfaces should be clean, free from oil, grease or other foreign matter.

**APPLICATION:**

Karnak #230-2% Neo-Asphalt can be applied to either concrete or macadam (blacktop) using a 1/16" serrated trowel. For best results, Karnak #230 2% Neo-Asphalt should be allowed to have a minimum of 2-3 hours open air time or until material becomes tacky and just skins over, prior to embedding the asphalt bricks.

**COVERAGE:**

Apply at the rate of 1.5 - 2 gallons per 100 sq. ft. Do not exceed coverage rate.

**CARE OF TOOLS:**

Tools and other equipment should be thoroughly cleaned with mineral spirits, taking necessary precautions when handling combustible materials.

**CAUTION:**

Do not use near open flame. Avoid breathing solvent fumes and prolonged contact with skin. Do not take internally. If swallowed, **do not** induce vomiting. Call a physician immediately. Keep out of reach of children. Keep container covered when not in use. **Do not thin.** Dispose of in an environmentally safe manner.

**PACKAGING:**

Available in 5 gallon pails and 55 gallon drums.

If further information is needed, contact Karnak Technical Services at 1-800-526-4236.

**KARNAK**

330 CENTRAL AVENUE, CLARK, NJ 07066 732-388-0300  
• 800-526-4236 • FAX: 732-388-9422 WEB:  
<http://www.karnakcorp.com>

CH0105