



Acrylic-Based White Coating Selection Guide

ASPHALT

Finish Coat

BEST

535QS
Enviro-
Lastic @
1.5
gal./100ft²

BETTER

501 Elasto-
Brite @
1.5
gal./100ft²

GOOD

529 Renu-
White @
1.5
gal./100ft²

Base Coat

405 Bond-
N-Shield
Base Coat
@ 1.5
gal./100ft²

*501
Elasto-Brite
@ 1.5
gal./100ft²

*529 Renu-
White @
1.5
gal./100ft²

*If area is ponding water 405
Bond-N-Shield Base Coat is
recommended in place of
listed base coating.

Roof Preparation

7 9 9 Wash - N - Prep Roof Cleaner
(1 qt. cleans approximately 1,600 sq.ft.)

METAL & CONCRETE

535QS
Enviro-
Lastic or
501 Elasto-
Brite or 529
Renu-White
@ 1.5
gal./100ft²

404
Corrosion
Proof Base
Coat @
1.5
gal./100ft²

Rusty
Metal

535QS
Enviro-
Lastic or
501 Elasto-
Brite or 529
Renu-White
@ 1.5
gal./100ft²

535QS
Enviro-
Lastic or
501 Elasto-
Brite or 529
Renu-White
@ 1.5
gal./100ft²

No Rust /
Concrete

SPRAY FOAM

535QS
Enviro-
Lastic or
501 Elasto-
Brite or 529
Renu-White
@ 1.5
gal./100ft²

535QS
Enviro-
Lastic @
1.5
gal./100ft²

Adhesion Test
Recommended

TPO, PVC HYPALON

535QS
Enviro-
Lastic or
501 Elasto-
Brite or 529
Renu-White
@ 1.5
gal./100ft²

406 Tru-
Grip Base
Coat @
1.5
gal./100ft²

Adhesion Test on
PVC Recommended

EPDM

535QS
Enviro-
Lastic or
501 Elasto-
Brite or 529
Renu-White
@ 1.5
gal./100ft²

535QS
Enviro-
Lastic @
1.5
gal./100ft²

507 SPC Primer
Wash @ 0.2
gal./100ft²