

107 Velvet Roof Coating

DESCRIPTION:

KARNAK 107 Velvet Roof Coating is a non-fibered specially formulated black coating for use on all types of smooth surface asphalt roofs. It is prepared from selected asphalts and is carefully mixed with refined solvents to form a heavy paint consistency. 107 Velvet Roof Coating will withstand the rigors of hot summer temperatures and provide excellent protection against the ravages of weather and corrosion.

SURFACE PREPARATION:

All surfaces should be swept clean of all dust, dirt or loose particles. Recommended application temperature is 40°F to 120°F. If applying at temperatures lower than 40°F, the substrate must be free of moisture and/or ice crystals. Repair all blisters, breaks and cracks with 19 Ultra Rubberized Flashing Cement and 34 Asphalt Saturated Fabric or 31 Fiberglass Membrane.

BRUSH APPLICATION:

107 Velvet Roof Coating is easily applied with a wide, fiber roof brush. Apply at the rate of 1 to 2 gallons per 100 sq. ft.

SPRAY APPLICATION:

107 Velvet Roof Coating can be sprayed efficiently on large areas with airless spray equipment. Apply at the rate of 1 to 2 gallons per 100 sq. ft.

COVERAGE:

Apply at the rate of 1 to 2 gallons per 100 sq. ft.

CAUTION:

Do not use near open flame. Avoid breathing solvent fumes and prolonged contact with skin. Do not take internally. If swallowed, **do not induce vomiting**. Call a physician immediately. Keep out of reach of children. Keep container covered when not in use. **Do not thin**. Dispose of in an environmentally safe manner. Cover air intakes during application and while drying.

COLD-PROCESS SYSTEMS AND COATINGS, EITHER EMULSION OR SOLVENT BASED, SHOULD ONLY BE INSTALLED ON DECKS WITH POSITIVE DRAINAGE.

PER NRCA, (NATIONAL ROOFING CONTRACTORS ASSOCIATION) "THE CRITERIA FOR JUDGING PROPER SLOPE FOR DRAINAGE IS THAT THERE BE NO EVIDENCE OF STANDING WATER ON THE DECK 48 HOURS AFTER IT STOPS RAINING."

PACKAGING:

Available in 5 gallon pails and 55 gallon drums.

If further information is needed, contact KARNAK Technical Services at 1-800-526-4236.

KARNAK

330 CENTRAL AVENUE, CLARK, NJ 07066
732-388-0300 • 800-526-4236 • FAX: 732-388-9422
WEB: <http://www.karnakcorp.com>