

198 Asphalt Roof Resaturant

DESCRIPTION:

KARNAK 198 Asphalt Roof Resaturant is a carefully prepared blend of selected asphalt, mineral fillers and selected penetrating oils. These penetrating oils soak into the existing roof mat to help rejuvenate the old asphalt. In addition, a thick layer of asphalt remains on the surface of the roof to protect it from the ultra-violet rays of the sun as well as serving as a binder for the replacement of the gravel or slag.

SURFACE PREPARATION:

Remove all loose gravel, dirt and dust from the roof by sweeping or power brooming. If existing gravel is to be reused, it must be washed free of silt. Recommended application temperature is 40°F to 120°F. If applying at temperatures lower than 40°F, the substrate must be free of moisture and/or ice crystals. Repair all blisters, breaks or holes in the roof with 19 Ultra Rubberized Flashing Cement and 34 Asphalt Cotton Fabric, 31 Fiberglass Membrane or #5540 Resat-Mat.

APPLICATION:

Brush: 198 Asphalt Roof Resaturant is easily applied when poured directly from the container and spread with a thick fiber roof brush at the rate of 7 to 8 gallons per 100 sq. ft. After application of 198 Asphalt Roof Resaturant is completed, gravel should be re-applied at the rate of 400 lbs. per 100 sq. ft.

Spray: 198 Asphalt Roof Resaturant is easily and efficiently applied on large areas with a standard mastic pump. The coating should be sprayed on in one coat at the rate of 7 to 8 gallons per 100 sq. ft. applied with a 50% overlap of the spray pattern so as to obtain a uniform and continuous film.

After application of 198 Asphalt Roof Resaturant is completed, gravel should be reapplied at the rate of 400 lbs. per 100 sq. ft.

CAUTION:

Do not use near open flame. Avoid breathing solvent fumes and prolonged contact with skin. Do not take internally. If swallowed, **do not induce vomiting**. Call a physician immediately. Keep out of reach of children. Keep container covered when not in use. **Do not thin**. Dispose of in an environmental safe manner. Cover air intakes during application and while drying.

KARNAK

330 CENTRAL AVENUE, CLARK, NJ 07066
732-388-0300 • 800-526-4236 • FAX: 732-388-9422
WEB: <http://www.karnakcorp.com>

Revised 12.14.18



198 Asphalt Roof Resaturant

COLD-PROCESS SYSTEMS AND COATINGS, EITHER EMULSION OR SOLVENT BASED, SHOULD ONLY BE INSTALLED ON DECKS WITH POSITIVE DRAINAGE.

PER NRCA, (NATIONAL ROOFING CONTRACTORS ASSOCIATION) “THE CRITERIA FOR JUDGING PROPER SLOPE FOR DRAINAGE IS THAT THERE BE NO EVIDENCE OF STANDING WATER ON THE DECK 48 HOURS AFTER IT STOPS RAINING.”

PACKAGING:

Available in 55 gallon drums and 5 gallon pails.

If further information is needed, contact KARNAK Technical Services at 1-800-526-4236.

KARNAK

330 CENTRAL AVENUE, CLARK, NJ 07066
732-388-0300 • 800-526-4236 • FAX: 732-388-9422
WEB: <http://www.karnakcorp.com>

Revised 12.14.18

