

230-2% Neo-Asphalt (Trowel Grade)

DESCRIPTION:

KARNAK 230-2% Neo-Asphalt is a cold applied, rubberized asphalt cement, designed especially for use as an adhesive for paving blocks and pressed asphalt bricks. Eliminates the need for a hot kettle.

SURFACE PREPARATION:

All surfaces should be clean, free from oil, grease or other foreign matter. Recommended application temperature is 40°F to 120°F. If applying at temperatures lower than 40°F, the substrate must be free of moisture and/or ice crystals.

APPLICATION:

230-2% Neo-Asphalt can be applied to either concrete or macadam (blacktop) using a 1/16" serrated trowel. For best results, 230 2% Neo- Asphalt should be allowed to have a minimum of 2-3 hours open air time or until material becomes tacky and just skins over, prior to embedding the asphalt bricks.

COVERAGE:

Apply at the rate of 1.5 - 2 gallons per 100 sq. ft. Do not exceed coverage rate.

PHYSICAL PROPERTIES:

Viscosity @ 25C:	30,000-40,000 C.P.S.
Specific Gravity @ 25C:	1.02
Weight per Gallon @ 25C:	8.5 lbs.
% Solids by Weight:	68%
Softening Point of Rubber Blend:	150F
% Inorganic Material:	18%
% Long Fiber	10%
% Neoprene	2% min.

CAUTION:

Do not use near open flame. Avoid breathing solvent fumes and prolonged contact with skin. Do not take internally. If swallowed, **do not** induce vomiting. Call a physician immediately. Keep out of reach of children. Keep container covered when not in use. **Do not thin.** Dispose of in an environmentally safe manner.

PACKAGING:

Available in 5 gallon pails and 55 gallon drums.

If further information is needed, contact KARNAK Technical Services at 1-800-526-4236.

KARNAK

330 CENTRAL AVENUE, CLARK, NJ 07066
732-388-0300 • 800-526-4236 • FAX: 732-388-9422
WEB: <http://www.karnakcorp.com>

