

## 237-2% Neo-Asphalt (brush grade)

### DESCRIPTION:

KARNAK 237-2% Neo-Asphalt is an asbestos-free cold applied, rubberized asphalt cement, designed especially as an adhesive for paving blocks and pressed asphalt bricks, eliminating the need for a hot kettle.

### SURFACE PREPARATION:

All surfaces should be clean, dry, free from oil, grease or other foreign matter. Recommended application temperature is 40°F to 120°F. If applying at temperatures lower than 40°F, the substrate must be free of moisture and/or ice crystals.

### APPLICATION:

237-2% Neo-Asphalt can be applied to either concrete or macadam (blacktop) using a brush or squeegee. For best results, allow a minimum of 2-3 hours open air time or until material becomes tacky and just skins over prior to embedding the paving blocks.

### COVERAGE:

Apply at the rate of 1.5 - 2 gallon per 100 sq. ft. Do not exceed coverage rate.

### PHYSICAL PROPERTIES:

Viscosity @ 25C:	12,000-18,000 C.P.S.
Specific Gravity @ 25C:	1.02
Weight per Gallon @ 25C:	8.1 lbs.
% Solids by Weight:	70%
Softening Point of Rubber Blend:	150F
% Inorganic Material:	6.5%
% Long Fiber	10%
% Neoprene	2% min.

### NOTE:

237-2% Neo-Asphalt should be thoroughly **mechanically mixed** prior to application. Macadam (blacktop) surfaces should be cured prior to applying 237-2% Neo-Asphalt.

### CAUTION:

Do not use near open flame. Avoid breathing solvent fumes and prolonged contact with skin. Do not take internally. If swallowed, **do not** induce vomiting. Call a physician immediately. Keep out of reach of children. Keep container covered when not in use. **Do not thin.** Dispose of in an environmentally safe manner.

### PACKAGING:

Available in 5 gallon pails and 55 gallon drums.

If further information is needed, contact KARNAK Technical Services at 1-800-526-4236.

# KARNAK

330 CENTRAL AVENUE, CLARK, NJ 07066  
732-388-0300 • 800-526-4236 • FAX: 732-388-9422  
WEB: <http://www.karnakcorp.com>