

168 Tar Roof Resaturant

DESCRIPTION:

KARNAK 168 Tar Resaturant is a heavy duty non-asbestos protective coating for long lasting, weather-resisting protection for tar and gravel roofs, scientifically compounded to provide a completely monolithic coating assuring years of added roof life. Prepared from highly refined coal tar pitch base and thoroughly mixed mechanically with rust inhibitive chromates.

SURFACE PREPARATION:

Remove all loose gravel, dirt and dust from roof by vacuuming, sweeping or power broom. Repair all blisters, breaks or holes with 170 Tar Cement and 5540 Resat-Mat or 31 Fiberglass Membrane.

SPECIFICATIONS:

Made with ASTM D-450A Type I
Fed. Spec. #RP-381 Type I
SS-C-540B

BRUSH APPLICATION:

168 Tar Roof Resaturant is easily applied with a wide, fiber brush at the rate of 7 to 8 gallons per 100 sq. ft. After application of 168 Tar Roof Resaturant is completed, clean, dry gravel should be re-applied at the rate of 400 lbs. per 100 sq. ft.

SPRAY APPLICATION:

Efficiently sprayed on large areas with standard mastic pump-type equipment. Apply at the rate of 7 to 8 gallons per 100 sq. ft. After application of 168 Tar Roof Resaturant is completed, gravel should be re-applied at the rate of 400 lbs. per 100 sq. ft.

COVERAGE:

Apply at the rate of 7 to 8 gallons per 100 sq. ft.

KARNAK

330 CENTRAL AVENUE, CLARK, NJ 07066
732-388-0300 • 800-526-4236 • FAX: 732-388-9422
WEB: <http://www.karnakcorp.com>

168 Tar Roof Resaturant

PHYSICAL PROPERTIES:

Solids, Fed Spec. No. 791:	57% - 58%
Spec. Gravity, Fed. Spec.SSR-406C, Method 209.2:	1.18
ASH Fed. Spec. SSR-C, Method 226:	5% Flash
Point, Fed. Spec.SSR-406C, Method 217.01:	185°F
Weight per Gal:	9.84 lbs.
Touch Dry at 77°F:	24 hrs.
Viscosity:	8000 cps
Serv. Temp:	20° - 160°F
Saturation:	35-C-540
1-6 Felts:	90%
7-8 Felts:	10%
Low Temp Flex (6 hrs. at 25°F):	Passes

CAUTION:

Do not use near open flame. Avoid breathing solvent fumes and prolonged contact with skin. Do not take internally. If swallowed, **do not induce vomiting**. Call a physician immediately. Keep out of reach of children. Keep container covered when not in use. **Do not thin**. Dispose of in an environmentally safe manner. Cover air intakes during application and while drying.

PACKAGING:

Available in 5 gallon pails and 55 gallon drums.

If further information is needed, contact KARNAK Technical Services at 1-800-526-4236.

KARNAK

330 CENTRAL AVENUE, CLARK, NJ 07066
732-388-0300 • 800-526-4236 • FAX: 732-388-9422
WEB: <http://www.karnakcorp.com>