

97 Fibered Aluminum Roof Coating

DESCRIPTION:

KARNAK 97 Fibered Aluminum Roof Coating is made of selected asphalts and pigment flakes of pure aluminum blended with refined solvents and reinforcing fibers for heavy duty service. When KARNAK 97 Fibered Aluminum Roof Coating is applied to the roof, the aluminum flakes leaf to the surface providing a reflective metallic shield over the base of the coating.

FEATURES, BENEFITS AND ADVANTAGES:

The advantages of this metallic aluminum shield are two-fold:

1. The asphaltic oils in the roof are protected from harmful intense rays of the sun by the reflective properties of the aluminum. Most of the sun's rays are reflected by this aluminum shield, thereby preventing these oils from being "cooked" out of the roof substrate. The coating, therefore, retains its resilient characteristics and will not prematurely crack or dry out.
2. During the hot summer months, KARNAK 97 Fibered Aluminum Roof Coating may help reduce indoor building temperatures and improve inside living and working conditions, by reflecting the sun's rays and reducing roof surface temperatures.

One coat of KARNAK 97 Fibered Aluminum Roof Coating will extend the life of modified bitumen membrane, not only by limiting fire-spread, (as indicated by the U.L. Class "A" Rating) but its high aluminum content and excellent reflectivity afford solar protection and weather durability.

Modified Bitumen: KARNAK 97 Fibered Aluminum Roof Coating is U.L. Class A rated over specified Modified Bitumen Systems, UL Listing #RI2I99 (N).

USES:

KARNAK 97 Fibered Aluminum Roof Coating helps reduce indoor building temperatures. It's ideal for use on modified bitumen membranes, metal corrugated roof decks, steep asphalt roofs that have aged for 90 days, or any KARNAK emulsion roof coating that has been allowed to cure for 3-5 days.

SURFACE PREPARATION:

Prepare all surfaces by sweeping clean of dust, dirt, oil and loose particles. Repair all cracks and blisters by spreading KARNAK 19 Ultra Rubberized Flashing Cement over the damaged area, then embed KARNAK Asphalt Cotton, Fiberglass, Poly-Mat or Resat-Mat reinforcement and apply another coat of KARNAK 19 Ultra Rubberized Flashing Cement over the entire patch. New asphalt roof surfaces should weather a minimum of 90 days before being coated over with

KARNAK

330 CENTRAL AVENUE, CLARK, NJ 07066
732-388-0300 • 800-526-4236 • FAX: 732-388-9422

WEB: <http://www.karnakcorp.com>



97 Fibered Aluminum Roof Coating

KARNAK 97 fibered Aluminum Roof Coating. However, KARNAK 97 Fibered Aluminum Roof Coating can be coated on roofs 3 to 5 days after KARNAK asphalt emulsion roof coatings have been applied. Badly weathered or alligatored asphalt surfaces should be primed with KARNAK 100 Non-Fibered Emulsion Primer or 220 Fibered Emulsion Roof Coating prior to coating with 97 Fibered Aluminum Roof Coating. Allow emulsion primer/coating to cure a minimum of 3-5 days before application of aluminum roof coating.

APPLICATION:

KARNAK 97 Fibered Aluminum Roof Coating should be spread uniformly over the roof surface. Care should be taken not to overwork the coating during application. This could have a damaging effect on the leafing of the aluminum. Pour the correct amount of aluminum roof coating to cover a given area and work it in one direction. Be sure to mechanically mix the aluminum roof coating thoroughly before using. KARNAK 97 Fibered Aluminum Roof Coating can be applied with a soft roof brush, roller or spray.

NOTE:

Discoloration will occur in areas where KARNAK 19 Ultra Rubberized Flashing Cement is not allowed to dry a minimum of 60 days. After 60 days, recommended application temperatures are 50°F and rising. Must not come in contact with any type of moisture within 24-48 hours after application.

COVERAGE:

Apply at the rate of 1 to 1.5 gallons per 100 sq. ft. DO NOT THIN.

SPECIFICATIONS:

ASTM D-2824 Type III (Non-Asbestos) TT-C-498C (except Non-Asbestos)

ASTM D-3805 Miami-Dade Approved, ASTM D-962 Type II.

Cool Roof Council Rating (CRRC)

Solar Reflectance:	Initial	0.63	3 year	0.55
Thermal Emittance:	Initial	0.46	3 year	0.53
SRI:	Initial	62	3 year	52

Note: Coating Modified Bitumen Membranes with Aluminum Coatings:

KARNAK recommends coating torch-applied modified bitumen membranes as soon as possible after the membrane is installed.

KARNAK

330 CENTRAL AVENUE, CLARK, NJ 07066
732-388-0300 • 800-526-4236 • FAX: 732-388-9422
WEB: <http://www.karnakcorp.com>



97 Fibered Aluminum Roof Coating

KARNAK's experience, laboratory and field tests, as well as NRCA, RCMA and ARMA reports, indicate that aluminum roof coating will reduce the combined effects of ultraviolet rays, heat and moisture, which, especially on APP modified bitumens, enhance exudation that can cause discoloring and delamination of any surface coating.

COLD-PROCESS SYSTEMS AND COATINGS, EITHER EMULSION OR SOLVENT BASED, SHOULD ONLY BE INSTALLED ON DECKS WITH POSITIVE DRAINAGE.

PER NRCA, (NATIONAL ROOFING CONTRACTORS ASSOCIATION) "THE CRITERIA FOR JUDGING PROPER SLOPE FOR DRAINAGE IS THAT THERE BE NO EVIDENCE OF STANDING WATER ON THE DECK 48 HOURS AFTER IT STOPS RAINING."

CAUTION:

Do not use near open flame. Material is for building exterior applications only. Avoid breathing solvent fumes and prolonged contact with skin. Do not take internally. If swallowed, **do not induce vomiting**. Call a physician immediately. Keep out of reach of children. Keep container covered when not in use. **Do not thin**. Dispose of in an environmentally safe manner. Cover air intakes during application and while drying.

PACKAGING:

Available in 1 gallon cans, 5 gallon pails and 55 gallon drums.

If further information is required, please contact KARNAK's Technical Service Department at 1-800-526-4236.

KARNAK

330 CENTRAL AVENUE, CLARK, NJ 07066
732-388-0300 • 800-526-4236 • FAX: 732-388-9422

WEB: <http://www.karnakcorp.com>

