

197 Karnastatic “Slaters” Cement

DESCRIPTION:

KARNAK 197 Karnastatic Cement is prepared from a blend of selected asphalts, special additives, mineral fibers and refined solvents. This composition is then passed through a high speed mixer which results in a smooth trowel-like-consistency in the finished product.

197 Karnastatic Cement dries to a firm and hard finish. Because of its rapid curing action, 197 Karnastatic Cement is dry to the touch in just a few hours.

USES:

Because 197 Karnastatic Cement will not run or sag on vertical surfaces, it is ideal for use on:

- Flashings and parapet walls.
- As a gutter liner for either metal or wooden gutters.
- Dampproofing exterior masonry walls.

SURFACE PREPARATION:

All surfaces should be clean and free of all dust, dirt, oil, grease, rust, loose paint, or other foreign matter.

COVERAGE RATE:

Apply by trowel to an average thickness of 1/8” (8 gallons per 100 sq. ft.).

SPECIFICATION:

ASTM D-4586 Type II Class I

CAUTION:

Do not use near open flame. Material is for building exterior applications only. Avoid breathing solvent fumes and prolonged contact with skin. Do not take internally. If swallowed, **do not induce vomiting**. Call a physician immediately. Keep out of reach of children. Keep container covered when not in use. **Do not thin**. Dispose of in an environmentally safe manner. Cover air intakes during application and while drying.

PACKAGING:

Available in 5 gallon pails.

If further information is needed, contact KARNAK Technical Services at 1-800-526-4236.

KARNAK

330 CENTRAL AVENUE, CLARK, NJ 07066
732-388-0300 • 800-526-4236 • FAX: 732-388-9422
WEB: <http://www.karnakcorp.com>