

66 Modified Bitumen Adhesive

DESCRIPTION:

KARNAK 66 Modified Bitumen Adhesive is a bituminous based adhesive sealant designed for the application and repair of SBS modified bitumen single-ply membranes and bituminous single-ply membranes. When properly utilized this product adheres the membrane and seals the laps to prevent water intrusion.

FEATURES, BENEFITS AND ADVANTAGES:

1. Easy to apply.
2. Eliminates the need for torches and kettles.
3. Excellent cure.
4. Tough, flexible, adhesive and cohesive film.
5. Excellent water and weather resistance.
6. Excellent general adhesive sealant.
7. Excellent lap cement.
8. Good U.V. resistance.
9. Complies with current VOC regulations.
10. Elastomeric, moves with substrate.

USES:

66 Modified Bitumen Adhesive Brush-Grade is used to adhere and repair SBS modified bitumen single-ply membranes, base and ply sheets, and bituminous single-ply membranes. 66 Modified Bitumen Adhesive Trowel-Grade can be used to seal and make repairs on existing modified applications and flashings on vertical surfaces, i.e. skylights, vents and pipes.

SURFACE PREPARATION:

All surfaces should be free from oil, grease, dirt and loose materials. All BUR surfaces should be patched and repaired with KARNAK 19 Ultra Rubberized Flashing Cement and KARNAK 31 Glass Membrane. Metal surfaces must have all rust and scales removed. Recommended application temperature is 40°F to 120°F. If applying at temperatures lower than 40°F, the substrate must be free of moisture and/or ice crystals.

APPLICATION:

Apply 66 Modified Bitumen Adhesive Brush Grade on **Horizontal** surfaces at a rate of approximately 1-2 gallons per 100 square feet; irregular surfaces may require slightly more material. Do not apply adhesive directly to decking or sheathing. On **Vertical** surfaces apply 66 Modified Bitumen Adhesive Trowel Grade at 1/8" thickness (approx. 8 gallons per 100 sq. feet.). 66 Modified Bitumen Adhesive may be applied by serrated squeegee, roller, brush or trowel. Application of one or multiple layer(s), allow a minimum of 15-20 minutes open air time before applying Cap Sheet or before each layer. Do not exceed 2 layers when installing with adhesive. **Cover all air intakes during application and while drying.**

KARNAK

330 CENTRAL AVENUE, CLARK, NJ 07066
732-388-0300 • 800-526-4236 • FAX: 732-388-9422
WEB: <http://www.karnakcorp.com>



66 Modified Bitumen Adhesive

Application thickness, temperature, and number of membranes dictate how long it will take for the product to fully dry. Please consult membrane manufacturer for specific information and installation regarding their product.

COVERAGE RATE:

Apply 66 Modified Bitumen Adhesive Brush Grade at the rate of 1 to 2 gallons per 100 sq. ft. On porous or irregular surfaces, 2 gallons per 100 sq. ft. may be required. 66 Modified Bitumen Adhesive Trowel Grade should be applied at 1/8" thickness (approx. 8 gallons per 100 sq. feet.)

SPECIFICATIONS:

ASTM D-3019 Type III

PHYSICAL PROPERTIES:

Weight per Gallon:	8.65
Shear Strength:	18 lbs./sq. in.
Peel Strength:	10 lbs./lin. in.
Elongation:	200%
Recovery:	80%
Cure Time:	24 to 48 hours @ 77°F
Application Temperatures:	40°F to 100°F

CAUTION:

Do not use near open flame. Material is for building exterior applications only. Avoid breathing solvent fumes and prolonged contact with skin. Excessive application may create blistering. Application at temperatures below 40°F may take longer to cure. Do not take internally. If swallowed, **do not induce vomiting**. Call a physician immediately. Keep out of reach of children. Keep container covered when not in use. **Do not thin**. Dispose of in an environmentally safe manner. **Insure that proper ventilation is maintained during application and drying to prevent solvent fumes from entering the building.**

PACKAGING:

Available in 5 gallon pails and 55 gallon drums.

If further information is needed, contact KARNAK Technical Services at 1-800-526-4236.

KARNAK

Revised 04.08.19

330 CENTRAL AVENUE, CLARK, NJ 07066
732-388-0300 • 800-526-4236 • FAX: 732-388-9422
WEB: <http://www.karnakcorp.com>

