

DAMPPROOFING

102 Asphalt Primer



Read Safety Data Sheet before using this product.

DESCRIPTION: 102 Asphalt Primer is a material composed of selected asphalts and refined solvents. It has good resistance to temperature change, yet dries to a tough film. 102 Asphalt Primer provides a firm base and better adhesion for the application of asphalt coatings. 102 Asphalt Primer is **not** to be used as a roof coating.

USES: 102 Asphalt Primer's uses include prime coat over brick, metal surfaces, gypsum, concrete block and cinder block. It is also used to coat interior faces of masonry walls above grade and for all back-up materials such as stone, brick and concrete.

SURFACE PREPARATIONS: All surfaces should be dry, clean and free from oil or grease, dust, dirt, loose paint or other foreign matter.

APPLICATION: 102 Asphalt Primer is easily applied by brush, roller or spray equipment. Recommended application temperature is 40°F to 120°F. If applying at temperatures lower than 40°F, the substrate must be free of moisture and/or ice crystals. Primer should be worked into all cracks, holes and crevices. Primer must be thoroughly dry to the touch (not wet) prior to coating applications.

COVERAGE RATE: Apply at the rate of 0.5 to 1 gallon per 100 sq. ft. (8-16 wet mils) depending upon the condition and porosity of the surface to be primed.

CAUTION: Do not use near open flame. Avoid breathing solvent fumes and prolonged contact with skin. Do not take internally. If swallowed, do not induce vomiting. Call a physician immediately. Keep out of reach of children. Store in a heated room and keep container covered when not in use. Do not thin. Dispose of in an environmentally safe manner. Cover air intakes during application and while drying. Exterior use only.

PACKAGING: Available in 5-gallon pails and 55-gallon drums.

If further information is needed, contact KARNAK Technical services at 800-526-4236.

PHYSICAL PROPERTIES & SPECIFICATIONS

Weight per Gallon: 7.85 lbs.

Solids by Weight: 72%Nominal

Solids by Volume: 66%Nominal

Color: Black

Application Temp.: 40°F to 120°F

Dry Time: 8 to 24 hours

Service Temp
(Cured Film): -40°F to 180°F

VOC Content: 270 g/L MAX