

ROOFING

197 Karnastatic "Slaters" Cement



Read Safety Data Sheet before using this product.

DESCRIPTION: 197 Karnastatic Cement is prepared from a blend of selected asphalts, special additives, mineral fibers and refined solvents. This composition is then passed through a high speed mixer which results in a smooth trowel-like-consistency in the finished product.

197 Karnastatic Cement dries to a firm and hard finish. Because of its rapid curing action, 197 Karnastatic Cement is dry to the touch in just a few hours.

USES: Because 197 Karnastatic Cement will not run or sag on vertical surfaces, it is ideal for use on:

- Flashings and parapet walls.
- As a gutter liner for either metal or wooden gutters.
- Dampproofing exterior masonry walls.

SURFACE PREPARATION: All surfaces should be dry, clean and free from oil or grease, dust, dirt, loose paint or other foreign matter.

APPLICATION: Spread 197 Karnastatic "Slaters" Cement to an average thickness of 1/8" (approximately 8 gallons per square) and press tightly into joints, seams or cracks. To repair large cracks or breaks, spread 197 Karnastatic "Slaters" Cement over the damaged area, then embed 34 Asphalt Saturated Cotton Fabric, 31 Fiberglass Membrane or 5540 Resat-Mat polyester reinforcement and re-apply another coat of 197 Karnastatic "Slaters" Cement over the entire patch. Recommended application temperature is 40°F to 120°F. If applying at temperatures lower than 40°F, the substrate must be free of moisture and/or ice crystals.

COVERAGE RATE: Apply each application at an average thickness of 1/8" (8 gallons per 100 sq. ft.)

CAUTION: Do not use near open flame. Avoid breathing solvent fumes and prolonged contact with skin. Do not take internally. If swallowed, do not induce vomiting. Call a physician immediately. Keep out of reach of children. Store in a heated room and keep container covered when not in use. Do not thin. Dispose of in an environmentally safe manner. Cover air intakes during application and while drying. For exterior use only.

PACKAGING: Available in 5-gallon pails.

If further information is needed, contact KARNAK Technical services at 800-526-4236.

PHYSICAL PROPERTIES & SPECIFICATIONS

Weight per Gallon: 9.1 lbs.

Solids by Weight: 67% Nominal

Solids by Volume: 55% Nominal

Color: Black

Application Temp.: 40°F to 120°F

Service Temp
(Cured Film): 15°F to 180°F

VOC Content: 340 g/L MAX

ASTM D4586 Type II Class I